



### SPECTRUMSTONE ASTM TESTING SPEC

Technical Characteristics	Test Standard	Test Result
Visible Abrasion Resistance	ASTM C1353	124.5 (lw)
Chemical Resistance	ASTM C650	Resistant
Stain Resistant	ASTM C1378	Resistant
Water Absorption	ASTM C97	0.06%
Flexural Strength	ASTM C880	3109 psi (dry), 3248 psi (wet)
Modulus of Rupture	ASTM C99	3222 psi (dry), 3371 psi (wet)
Density	ASTM C97	147.9 lb/ft <sup>3</sup>